




TWISTED POLYETHYLENE



We produce Polyethylene Twisted Netting in the following twine references:

Ref. ^a	Diameter mm	Runnage m/Kg	Breaking Strength Kgf
10/9	1,1	1950	20
10/12	1,3	1350	28
10/15	1,4	1150	32
10/18	1,5	980	38
10/21	1,7	840	45
10/24	1,8	720	53
10/27	1,9	625	58
10/30	2,0	540	64
10/36	2,2	450	78
10/39	2,3	400	88
10/45	2,5	350	100
10/60	3,0	290	120
15/60	3,5	140	215



Rev/07/2015

This data is for guidance purposes only and subject to changes without prior notice.

Lankhorst Euronete Portugal, SA
Rua da Cerfil (Cap. Gramaxo) PO Box 1029
4471-909 Maia - Portugal

Phone: +351 229 619 200
Fax: +351 229 605 757
e-mail: euronetesalesdepartment@lankhorsteuronete.com

